

CREDO

CREDO

crevin
efficiency



Composición / Composition	55%PP 39%PES 6%CO	
Ancho / Width	140	
Gramaje Lineal / Linear Weight	750 gr/ml \pm 5%	
Resistencia al deslizamiento de las costuras (mm) Seam slippage resistance (mm)	URD / WARP	TRM / WEFT
	2	1,6
Resistencia a la abrasión Abrasion resistance	Rotura hilo (A) / Repelado chenilla (B) End point (A) / Fully worn off (B)	>100.000 (A)
	Cambio aspecto 3000c Change aspect 3000c	4-5
Resistencia al pilling / Pilling resistance	4-5	
Reacción al fuego* Assessment of ignitability*	BS5852 Sche. Part 4 Source 0	PASA / PASS
	EN 1021 Part 1	PASA / PASS
	CAL TB 117:2013	PASA / PASS
	NFPA 260:2013	PASA / PASS
<small>* Bajo solicitud / Upon request: BS5852 Sche. Part 4 Source 1, EN 1021 Part 2, BS7176 Low Hazard, UNI 9175 3M</small>		
Solidez a la luz artificial / Lightfastness	6	
Solidez al frote / Colour fastness to rubbing	SECO / DRY	HUM / WET
	4-5	4-5
Condiciones de lavado / Washing conditions		

Sostenibilidad / Sustainability

23% hilo reciclado
23% recycled content

Cero residuos
Zero waste

Libre de biocidas y PFCs
Biocide and PFCs free

OEKO-TEX®
CONFIDENCE IN TEXTILES
STANDARD 100
20200K0217 AITEX



MADE IN EUROPE

Made by Crevin
www.crevin.com

CREDO 54 / 02